

U-MIX® Sand Mix

60 lb / 80 lb Bags

#67744 / #67732

DESCRIPTION:

U-MIX® Sand Mix is a specially formulated blend of Portland cement and sand idea for use where a thickness of one to two inches is required. All ingredients are thoroughly premixed to ensure maximum strength and work-ability. Simply add water. Achieves 3500 PSI compressive strength as required in ASTM C-387 when used as directed.



SUGGESTED USES:

- Concrete Floor Topping
- Parging
- Repairing Walls
- Grouting
- Laying Flagstone & Paving
- Fill Cracks
- Stuccoing
- Floor Repair

PREPARATION:

All surfaces should be clean and free of oil, gas, paint, grease, etc. before applying mix. Smooth surfaces should be roughened with a wire brush.

DIRECTIONS FOR MIXING:

Pour U-MIX® Sand Mix into a clean wheelbarrow, mortar box, or mixing bucket. Form a crater in the center of the dry mix. Pour clean potable water into the crater at a rate of one quart per 15 pounds of mix. Work the mix with a shovel or hoe adding water as needed to achieve a stiff moldable mixture. Avoid over wetting the mix. Adding excessive water may weaken the mix.

FOR BEST RESULTS:

Use only when temperature is 40° and rising. In cold weather use warm, not hot, water for mixing.

Apply freshly mixed U-MIX® Sand Mix immediately. Do not retemper the mix after initial mixing.

When patching or resurfacing, it is important to dampen the surface of the existing concrete before applying the new material. The use of quality bonding agents is recommended.

Allow the new concrete to set firmly, then keep moist for at least three (3) days by applying an occasional fine spray with water. Covering the surface with plastic film or damp burlap is also beneficial.

60 lb BAG COVERAGE:

60 lb bag yields approximately 6 ft² x 1" thick or ½ ft³ wet volume.

TOOLS YOU MAY NEED:

- Wheelbarrow or Mixer
- Trowel and/or Float
- Shovel or Hoe

CLEAN UP:

Clean up is easy and simple with soap and water. Rinse tools before materials hardens.

80 lb BAG COVERAGE:

80 lb bag yields approximately 8 ft² x 1" thick or ⅔ ft³ wet volume.